

# PRO-PRINT (Clear Matte) Heat Transfers

Pro-Print (Clear Matte) Heat Transfers are created out of a durable, polyurethane based material, soft hand, highly flexible, gloss finish and scratch, crack, fade and UV resistant. These heat transfers out-perform screen-printing. They are certified for no harmful substances, and are free from PVC, plasticizers, and heavy metals. Pro-Print (Clear Matte) Heat Transfers allow you to create professional, personalized garments quickly, easily and cost-effectively. Available as transfers (no minimum purchase requirement) and roll good form (minimum purchase of 1 roll - 30" x 30 yds).

## Application Instructions

Heat Transfer Machine Settings:

Temperature: 280-300°F (138-150°C)

Pressure: 40-60 PSI or 2-4 bar (Medium)

### Step 1:

Preheat garment/panel 10-15 seconds prior to application of transfer.

### Step 2:

Place heat transfer onto garment/panel. Cover with kraft or teflon paper. Using heat transfer settings, apply transfer for 5 seconds. Peel cold.

### Step 3:

Remove heat transfer liner carefully. Cover with kraft or teflon paper and apply for another 5 seconds.

## Recommended Fabrics:

100% Cotton

100% Polyester

Poly/cotton Blends

Polyester knits and mesh

## Care Instructions:

Machine wash using mild detergent.

Wash temperature should not exceed 175°F (80°C)

Do not use bleach.

Dry at normal setting on household machines.

Do not commercial launder.

Do not dry clean.

Do not iron directly onto heat transfer.

ALL GUIDELINES AND TECHNICAL INFORMATION ARE BASED ON WHAT WE BELIEVE TO BE ACCURATE. HOWEVER WE CANNOT GUARANTEE PERFORMANCE OF THE PRODUCT NOT UNDER THE MANUFACTURER'S CONTROL. PLEASE DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS END USE. THE USER ASSUMES ALL RISK AND LIABILITY WITH RESPECT TO THE USE OF THIS PRODUCT. WE WILL ONLY REPLACE GOODS DETERMINED BY THE SELLER AND MANUFACTURER AS DEFECTIVE.



Copyright © 2014

**Block Bindings  
& Interlinings Ltd**

9500 Rue Meilleur, Suite 402  
Montreal, Quebec H2N 2B7

T. (514) 381-7493

F. (514) 381-6725